



690 Sunol Street - San Jose, CA 95126  
8280 14<sup>th</sup> Ave. - Sacramento, CA 95826

(408) 287-1400  
(916) 454-2560



## OverKote<sup>®</sup> Bumper Adhesive

### DESCRIPTION:

A homogeneous mixture of refined petroleum asphalt emulsion, and selected fillers & binders. A one-component product formulated for use in adhering concrete blocks to asphaltic surfaces without the need of metal rods or pins.

### MATERIAL SPECIFICATIONS

#### **SPECIFICATIONS**

Residue, % by Weight  
Pressure Sensitivity

#### **LIMITS**

76 minimum

#### **TEST METHODS**

See Note 1  
Hold in place immediately;  
develop tenacious bond  
upon setting.

NOTE 1: Weigh 25 grams of the sample in a tared friction top can lid about 5" in diameter and spread uniformly over its surface. Heat the lid with its contents in an oven at 95-100°C (221-230°F) for 24 hours. cool and weigh. From the weight of the residue left in the lid and from the weight of the original sample, compute the percentage of nonvolatile matter.

### PREPARATION:

Surface areas shall be free of dust and dirt.

### APPLICATION:

Apply sufficient amount of material so that when bumper is put into place, adhesive is visible around all bottom edges.

### COVERAGE:

Indefinite. Surface texture will cause coverage rate to vary.

### PRECAUTIONS:

Air temperature shall be at least 55°F and rising. Wash tools in water. Use paint thinner if material has dried. Keep from freezing. Do not store in direct sunlight or where temperatures exceed 100°F. Container should be closed when not in use. Keep out of reach of children.

### PACKAGING:

5 gallon pails

Due to the wide range of variables affecting the results of application, such as weather conditions, construction equipment, and quality of other materials, there is no warranty, expressed or implied, that following this specification, or using the materials covered thereby, will assure satisfactory results.

**MATERIAL SAFETY DATA SHEETS AVAILABLE ON REQUEST**