



RG16N Nonwoven Geotextile Technical Data Sheet

Reed & Graham's RG16N is a nonwoven geotextile composed of polypropylene fibers, which are formed into a stable network such that the fibers retain their relative position. RG16N is inert to biological degradation and resists naturally encountered chemicals, alkalis, and acids.

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value
Grab Tensile Strength	ASTM D 4632	kN (lbs)	1.69(380)
Grab Tensile Elongation	ASTM D 4632	%	50
Trapezoid Tear Strength	ASTM D 4533	kN (lbs)	0.644(145)
CBR Puncture Strength ¹	ASTM D 6241	kN(lbs)	4.82 (1080)
Apparent Opening Size (AOS) ²	ASTM D 4751	mm (U.S. Sieve)	0.15 (100)
Permittivity	ASTM D 4491	Sec ⁻¹	0.7
Flow Rate	ASTM D 4491	l/min/m ²	2035
		(gal/min/ft ²)	50
UV Resistance after 500 hours	ASTM D 4355	% Strength Retained	70

¹ ASTM D 6241 replaces ASTM D 4833.

² ASTM D 4751, AOS is a Maximum Opening Diameter Value.

PLEASE NOTE: Mullen Burst Strength ASTM D 3786 is not recognized by ASTM D-35 on Geosynthetics as an acceptable Geosynthetic test methods. Puncture Strength ASTM D 4833 is not recognized by AASHTO M288 and has been replaced with CBR Puncture ASTM D 6241

Physical Properties	Test Method	Unit	Typical Value
Weight	ASTM D5261	g/m2 (oz/yd2)	441 (13)
Roll Dimension (width x length)		M	4.5 x 45
		ft	(15 x 150)
Roll Area		M2 (yd2)	209 (250)
Estimated Roll Weight		Kg (lb)	93 (205)

Disclaimer: Reed & Graham assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Reed & Graham disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

November 14, 2011